



Plastiment® 130

High Performance Plasticiser

Technical Data Sheet

DESCRIPTION

Plastiment 130 is a purpose designed chemical combination of Modified Lignosulphonates.

Plastiment 130 allows the manufacture of economic high quality concrete without undesirable side effects.

Plastiment 130 is a ready to use liquid for producing a more uniformly cohesive quality concrete to meet the specifications and needs of Architects, Consulting Engineers and Contractors.

USES

- * Readymix concrete
- * Precast concrete
- * Pumped concrete
- * Lightweight concrete
- * Wet shotcrete
- * Semi-dry concrete

ADVANTAGES

- * Improved workability/reduces w/c ratio
- * Flexible high performance plasticiser
- * High resistance to segregation/reduces bleeding
- * Improved surface finish
- * Reduces shrinkage cracking potential
- * Higher initial and ultimate compressive strengths
- * Higher durability concrete
- * Minimal effect on set retardation, even at maximum stated dose

Technical Data (typical)

Form:	Liquid
Colour:	Brown
Specific gravity:	1.2 @ 20°C
Air entrainment:	Slight controlled increase, less than 2% additional air is entrained
Chloride content % w/w:	Nil (to BS5075)
Effect on setting:	Slight increase in retardation
Freezing point °C:	-1°C

This product complies to EN 934-2 T2.

All above values are approximate.



METHOD OF USE

For maximum dispersion **Plastiment 130** should be added with the mixing water, on no account should it be added to the dry cement. Where concrete is being mixed by ready mixed trucks, **Plastiment 130** can be added at the batching plant but the trucks must rotate their drums until a uniform mix is achieved. To produce flowing concrete a well proportioned pump mix should be used.

PACKAGING

Plastiment 130 is supplied in 25 litre, 200 litre and 1000 litre containers. Bulk deliveries can be arranged.

STORAGE AND SHELF LIFE

The product should be stored away from extremes of temperature and should be protected from frost. Storage life 12 months minimum from delivery.

DOSAGE

The dosage rate of **Plastiment 130** is best found after initial site trials, which will take into consideration the best performance/dosage rate. As a guide an addition rate of between 0.3-0.5% by weight of cement is recommended (i.e. 0.15-0.25 litres per 50kg).

COMPATIBILITY

Can be used with all types of Portland Cements and **Sika** Admixtures. It is recommended that admixtures are added to the concrete separately

COMPRESSIVE STRENGTH RESULTS (typical):

Admixture	Dose (M1/50kg Cement)	w/c ratio	C.F.	Air Cont %	28 day Compressive Strength N/mm ²
Control	None	0.60	0.89	0.4	32.5
Plastiment 130	150	0.59	0.87	0.5	41.5



Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED
 Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ
 Tel: 01707 394444 Email: sika@uk.sika.com Fax: 01707 329129 www.sika.com





Plastiment® 160

High Performance Plasticiser

Technical Data Sheet

DESCRIPTION

Plastiment 160 is a purpose designed chemical combination of Modified Lignosulphonates.

Plastiment 160 allows the manufacture of economic high quality concrete without undesirable side effects.

Plastiment 160 is a ready to use liquid for producing a more uniformly cohesive quality concrete to meet the specifications and needs of Architects, Consulting Engineers and Contractors.

Plastiment 160 conforms to BS5075 Pt 1, 1982.

USES

- * Readymix concrete
- * Precast concrete
- * Pumped concrete
- * Lightweight concrete
- * Wet shotcrete
- * Semi-dry concrete

ADVANTAGES

- * Improved workability/reduces w/c ratio
- * Flexible high performance plasticiser
- * High resistance to segregation/reduces bleeding
- * Improved surface finish
- * Reduces shrinkage cracking potential
- * Higher initial and ultimate compressive strengths
- * Higher durability concrete
- * Minimal effect on set retardation, even at maximum stated dose.

Technical Data (typical)

Form:	Liquid
Colour:	Brown
Specific gravity:	1.2 @ 20°C
Air entrainment:	Slight controlled increase, less than 2% additional air is entrained
Chloride content % w/w:	Nil (to BS5075)
Effect on setting:	Slight increase in retardation
Freezing point °C:	-1°C
This product complies to EN 934-2 T2.	
All above values are approximate.	



METHOD OF USE

For maximum dispersion **Plastiment 160** should be added with the mixing water, on no account should it be added to the dry cement. Where concrete is being mixed by ready mixed trucks, **Plastiment 160** can be added at the batching plant but the trucks must rotate their drums until a uniform mix is achieved. To produce flowing concrete a well proportioned pump mix should be used.

PACKAGING

Plastiment 160 is supplied in 25 litre, 200 litre and 1000 litre containers. Bulk deliveries can be arranged.

STORAGE AND SHELF LIFE

The product should be stored away from extremes of temperature and should be protected from frost. Storage life 12 months minimum from delivery.

DOSAGE

The dosage rate of **Plastiment 160** is best found after initial site trials, which will take into consideration the best performance/dosage rate. As a guide an addition rate of between 0.3-1.5% by weight of cement is recommended (i.e. 0.15-0.75 litres per 50kg).

COMPATIBILITY

Can be used with all types of Portland Cements and **Sika** Admixtures. It is recommended that admixtures are added to the concrete separately

COMPRESSIVE STRENGTH RESULTS (typical):

Admixture	Dose (M1/50kg Cement)	w/c ratio	Slump (mm)	Air Cont %	28 day Compressive Strength N/mm ²
Control	None	0.54	55	-	41.5
Plastiment 160	200	0.49	60	-	55.0

Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED
 Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ
 Tel: 01707 394444 Email: sika@uk.sika.com Fax: 01707 329129 www.sika.com





Plastiment® 170

High Performance Plasticiser

Technical Data Sheet

DESCRIPTION

Plastiment 170 is a purpose designed material which is a chemical combination of Modified Lignosulphonates.

Plastiment 170 allows the manufacture of economic high quality concrete without undesirable side effects.

Plastiment 170 is a ready to use liquid for producing a more uniformly cohesive quality concrete to meet the specifications and needs of Architects, Consulting Engineers and Contractors.

Plastiment 170 conforms to BS5075 Pt 1, 1982.

USES

- * Readymix concrete
- * Precast concrete
- * Pumped concrete
- * Lightweight concrete
- * Wet shotcrete
- * Semi-dry concrete

ADVANTAGES

- * Improved workability/reduces w/c ratio
- * Flexible high performance plasticiser
- * High resistance to segregation/reduces bleeding
- * Improved surface finish
- * Reduces shrinkage cracking potential
- * Higher initial and ultimate compressive strengths
- * Higher durability concrete

Technical Data (typical)

Form:	Liquid
Colour:	Brown
Specific Gravity:	1.21 @ 20°C
Air entrainment:	Slight controlled increase, less than 2% additional air is entrained.
Chloride Content % w/w:	Nil (<0.1%)
Effect on Setting:	Slight increase in retardation
Compatibility:	Can be used with all types of Portland Cements and Sika Admixtures. It is recommended that admixtures are added to the concrete separately.
Freezing Point °C:	-1°C

This product complies to EN 934-2 T2.



All above values are approximate.

For maximum dispersion **Plastiment 170** should be added with the mixing water, on no account should it be added to the dry cement. Where concrete is being mixed by ready mixed trucks, **Plastiment 170** can be added at the batching plant but the trucks must rotate their drums until a uniform mix is achieved. To produce flowing concrete a well proportioned pump mix should be used.

DOSAGE

The dosage rate of **Plastiment 170** is best found after initial site trials, which will take into consideration the best performance/dosage rate. As a guide an addition rate of between 0.3–0.5% by weight of cement is recommended (ie 0.15–0.25 litres per 50 Kg).

PACKAGING

Plastiment 170 is supplied in 25 litre, 200 litre and 1000 litre containers. Bulk deliveries can be arranged.

STORAGE AND SHELF LIFE

The product should be stored away from extremes of temperature and should be protected from frost. Storage life 12 months minimum from delivery.

Compressive Strength Results (typical):

Admixture	Dose (M1/50 Kg Cement)	w/c ratio	Slump (mm)	Air Cont %	28 day Compressive Strength N/mm ²
Control	None	0.65	75	0.8	42.5
Plastiment 170	200	0.59	80	1.5	54.0

Effect on Workability (typical):

Admixture	Dose (M1/50 Kg Cement)	w/c ratio	Slump (mm)	Air Cont %	28 day Compressive Strength N/mm ²
Control	None	0.65	75	0.8	42.5
Plastiment 170	200	0.65	Collapsed	1.5	43.0

Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

