

Substructure Waterproofing - Membranes

Bituthene® 8000

Advanced, self-adhesive water and vapour proof membrane for sub-structures

Description

Bituthene® 8000 combines the proven Bituthene adhesive technology with a unique, grey coloured carrier film to provide superior performance and easier installation. Bituthene 8000 is extremely tough but any accidental damage which would otherwise be missed, is made visible by the black compound showing through the light grey film.

Installation

At air temperatures below +5°C measures should be taken to ensure that all surfaces are free from ice or frost.

All surfaces except those below ground bearing slabs and Preprufe® R membranes should be primed with one coat of Grace's water-based primer - Bituthene Primer W2, which is suitable for use on damp surfaces. Bituthene Primer W2 can be applied by brush or roller.

Alternatively, if time is critical, Grace's solvent based primer - Bituthene Primer S2, which can be used to allow priming and installation of membrane on damp surfaces or "green" concrete. Bituthene Primer S2 can be applied by brush or roller.

The drive for continual improvements in performance may result in product modifications. Your Grace representative will be able to provide up-to-date advice.

Bituthene 8000 shall be laid by peeling back the protective release paper and applying the adhesive face onto the prepared surface, free from ice, frost or condensation. Bituthene LM to be applied at all internal and external

Advantages

- **Water and vapour proof** - provides protection for all basements, BS 8102:2009.
- **Gas resistant** - methane, Carbon dioxide and radon gas protection in excess of the standard membrane requirements in BRE Reports 211 (radon) and 212 (methane and carbon dioxide).
- **Superior performance** - 70 m hydrostatic pressure resistance with ultra low moisture transmission rate.
- **Wide application "window" reduces delays** - application temperature range from -10°C to +35°C and damp surface tolerant.
- **Easier handling in warm weather** - over 20% reduction of solar heat absorption.
- **Unique composite film** - engineered for strength, flexibility and a smooth finish.
- **Facilitates quality assured installation** - printed overlap line ensures minimum laps; light grey colour highlights accidental damage for simple patch repairs.
- **System Compatibility** - can be combined with Preprufe® pre-applied membranes, Bituthene® LM, and Hydroduct® for system solutions.


corners, penetrations etc. prior to applying the overall membrane. Bituthene 8000 should be brushed onto the surface to ensure good initial bond and exclude air. Adjacent rolls are aligned using printed lines and overlapped 50 mm minimum at side and ends and well rolled with a firm pressure, using a lap roller to ensure complete adhesion and continuity between the layers. On high walls it may be necessary to batten fix the membrane to prevent slippage. Once the membrane is applied, cover with a protection board as soon as possible. On "green" concrete or damp surfaces, cover the membrane immediately.

Repairs, Protection & Drainage

- Damaged areas to be repaired with an oversize patch applied to a clean dry surface extending 100 mm beyond damage and firmly rolled.
- The membrane should be protected against damage using Grace Protection 03 boards bonded to the membrane using Bitustik 4000 double sided tape or Pak Adhesive and firmly rolled.
- If the area around the substructure can be drained to a low level outlet then Grace recommends the Hydroduct range of drainage membranes.

Performance

Bituthene 8000 complies with the following national standards: BS 8102: 2009, The Building Regulations (as amended) (England and Wales) 2000, The Building Regulations (Northern Ireland) 2000 (as amended), Building Standards (Scotland) Regulations 2004 (as amended).




Details shown are typical illustrations only and not working drawings. For assistance with working drawings and additional technical advice please contact Grace Technical Services



Supply

Bituthene® 8000	1 m x 20 m roll (20 sq m) Weight 36 kg
Storage	Store upright in dry conditions below +30°C
Bituthene® Primer W2	5 litre can
Coverage	7-8 sq m per litre
Bituthene® Primer S2	5 & 20 litre can
Coverage	10-12 sq m per litre (depending upon method of application, surface porosity and ambient temperature)
Ancillary Products	
Bituthene® LM	5.7 litre packs
Bituthene® Protection boards	3 mm x 0.9 m x 2.03 m (± 6%)
Adcor® 500S	6 x 5 m rolls
Adcor® 550MI	8 x 5 m rolls
Bitustik™ 4000	150 mm x 12 m roll
Pak Adhesive	5 litre can
Hydroduct®	Refer to data sheet for Hydroduct Vertical Drainage Sheets.

Equipment by others: Lap Roller

	Grace Construction Products Ltd Ipswich Road, Slough, Berkshire SL1 4EQ United Kingdom 06 06/F017
	EN 13967 Bituthene® 8000 Flexible Sheets for Waterproofing, Type T Reaction to fire: E Watertightness: Pass at 60 kPa

Declared values according to EN 13967

Property	Declared Value	Test Method	Property	Declared Value	Test Method
Visible defects - MDV	No	EN 1850-2	Straightness - MDV	Pass	EN 1848-2
Length (m) - MDV	20.15 ± 0.15	EN 1848-2	Thickness (mm) - MDV	1.52 ± 0.08	EN 1848-2
Width Carrier Sheet (m) - MDV	0.987 ± 0.007	EN 1848-2	Mass per unit area (g/m²) - MDV	1490 ± 90	EN 1848-2
Width Overall (roll) (m) - MDV	1.000 ± 0.005	EN 1848-2	Durability of water tightness against ageing/degradation (at 60 kPa)	Pass	EN 12691 EN 1928
Water tightness to liquid water (at 60 kPa)	Pass	EN 1928	Durability of water tightness against chemicals (at 60 kPa)	Pass	EN 12691 EN 1928
Resistance to impact (AI-board) (mm) - MLV	150 - Pass	EN 12691	Durability of tensile properties against chemicals	Pass	EN 13967 Annex C
Resistance to impact (base EPS) (mm) - MLV	1000 - Pass	EN 12691	Compatibility with bitumen	Pass	EN 1548
Resistance to tearing (Nail Shank) - unreinforced sheets (N) - MLV	Long ¹ 110 Trans ² 100	EN 12310-1	Resistance to static loading	Pass	EN 12730
Joint strength (N/50mm) - MLV	190	EN 12317-1	Tensile properties - unreinforced sheets (N/6mm) - MLV	Long ¹ 25 Trans ² 25	EN 12311-2 Method B
Water vapour transmission (μ = sD/d) - MDV	103.000 - 110.000	EN 1931 Method B	Tensile properties - unreinforced sheets (Elongation %) - MLV	Long ¹ 20 Trans ² 20	EN 12311-2 Method B
Resistance to deformation under load	NPD ⁵	EN 13967 Annex B	Reaction to fire (Class; test conditions)	E	EN 13501-1

Footnotes: 1. Longitudinal - related to the roll direction 2. Transversal - related to the roll direction
3. MDV: Manufacturer Declared Value 4. MLV: Manufactured Limiting Value 5. NPD: No Performance Declared

All declared values shown in this data sheet are based on test results determined under laboratory conditions and with the product sample taken directly from stock in its original packing without any alteration or modification of its component parts.

www.graceconstruction.com

Grace Construction Products Limited Ipswich Road Slough Berkshire SL1 4EQ United Kingdom
Tel +44 (0)1753 490000 Fax +44 (0)1753 490001

Adcor, Bituthene, Hydroduct and Preprufe are registered trademarks of W R Grace & Co.-Conn. Bitustik is a trademark of W R Grace & Co.-Conn.

The information given is based on data and knowledge considered by GRACE to be true and accurate and is offered for the user's consideration, investigation and verification only. Since the conditions of use are beyond our control we do not warrant the results to be obtained. None of these statements, recommendations or suggestions shall constitute a warranty, guarantee, representation or statement of similar legal nature. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party. This data sheet should be checked against the latest version available from the local GRACE Representative or the GRACE website. The information contained in the latest data sheet supersedes all previously published editions. Visits to site by GRACE personnel do not constitute supervisory responsibility.

These products may be covered by patents or patents pending.

Copyright 2011. Grace Construction Products Ltd B8000/UK/003a Printed in UK 09/11

Health and Safety

There is no legal requirement for a Material Safety Data Sheet for Bituthene 8000, Bituthene Protection Boards, Bitustik 4000 or Hydroduct. Refer to product carton for additional safety information. For health and safety questions on these products please contact Grace Construction Products Limited.

For Bituthene Primer W2, Bituthene Primer S2 and Bituthene LM read the product label and Material Safety Data Sheet (MSDS) before use. Users must comply with all risk and safety phrases. MSDS's can be obtained from Grace Construction Products.

Specification Clause

Refer to Clause 180 and 190.

Physical Properties

Property	Typical Value	Test Method
Colour	Dark grey-black	
Resistance to hydrostatic head	>70 m of water	ASTM D5385
Methane Permeability (note 1)	89.52 ml/m ² .day.atm	Versapern Ltd
Radon Diffusion Coefficient	6.8 x 10 ⁻¹³ m ² /s	University of Prague

Note 1: Typical value for BRE recommended minimum standard (BRE Report 212) is 360 ml/m²/day.

GRACE