






CUPA 5

Non-carbonated **slate** formed by tectonic compression.
Dark grey slate with a **riven surface**.


 Quarry Valdacal. Puzmazán (Ourense) Spain.

 Operating since 1971.

 Sizes: 20x20 - 60x45 cm
Thickness: 5 - 6.5 - 7.5 - 9 mm



Formats



Selections



Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,21% Code: W1 (< 0,4%)	0,27% Fullfil (< 2%)	Longitudinal 37 MPA	S1	T1	Fullfil < 0,4%

International certifications



European Standard: EN 12326 | French Specifications: NF 228-02/01/01 | Belgian Specifications: ATG/H848 | British Standard: BS 680 Part 2