

SANDEX FINE TEXTURED MATT

Sandtex Trade Fine Textured Matt is the original fine textured masonry paint, independently endorsed by the British Board of Agreement to last 15 years. By applying two full coats of Sandtex Trade Fine Textured Matt and, where necessary, products such as Sandtex Trade Fungicide and Sandtex Trade Stabilising Solution, you are assured of a professional quality finish and long lasting protection.

AVAILABILITY

Colour range Refer to current Sandtex Trade Literature

Packaging 5 and 10 litres

PROPERTIES

Drying time Under normal drying conditions recoatable after 4-6 hours.

Finish Matt, very finely textured.

Composition Pigment: Titanium Dioxide, light fast coloured pigments and extenders
Resin: VaVeOVA Copolymer
Solvent: Water

Spreading rate 7m² per litre. on prepared smooth surfaces. On textured surfaces the spreading rate could reduce to approximately 3m² per litre.

Wet film thickness 143 micrometres at 7m² per litre.

Dry film thickness 58 micrometres at 7m² per litre.

Volume solids 41% Brilliant White other colours will vary.

Flash point Not applicable

VOC content EU limit value for this product (cat.A/c): 75 g/l (2007)/40g/l (2010)
This product contains max. 20 g/l VOC.

Limitations Do not apply when there is a risk of rain, air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period. Do not apply to bitumen coatings. The decoration of Fletton brickwork either facings or commons is not recommended.

PREPARATION

New surfaces All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the material to be applied.

For surfaces with suction (porous surfaces), dilute the first coat with up to 40% clean water to satisfy surface suction and allow to dry.

Previously decorated surfaces

All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose and failing or suspect material by scraping or brushing with a stiff bristle brush (not wire) to a sound edge. Organic growth must be removed and the areas treated with Sandtex Trade Fungicide. For surfaces in poor condition mechanical means may be necessary e.g. pressure washing between 1500-2000 psi (102-136 bar), wet or dry grit blasting, or a

proprietary paint removal system. Care must be taken not to damage the underlying surface.

Fill cracks and surface defects in masonry surfaces with Sandtex Trade Exterior Easiplast and finish to match existing finish. Stabilise all bare, filled and previously decorated chalking areas with an application of Sandtex Trade Stabilising Solution. Wash any soundly adhering gloss painted surfaces with hand hot water and liquid detergent solution to remove any contaminants frequently changing the water. Wet abrade any glossy areas to provide a key. Rinse thoroughly with clean water to remove all residues, and allow to dry.

COATING SYSTEM

Apply two full coats as required.

APPLICATION

Stir well before use. Apply by brush, medium or long pile roller depending on surface textured. Not suitable for use by airless spray.

CLEANING

Return surplus material to container. Wash with clean water immediately after use.

HEALTH AND SAFETY

Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing the surfaces avoid the inhalation of dust. Wear a suitable facemask. Material Safety Data Sheets for this and all other Sandtex products are freely available from the place of purchase or the address below. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Final results cannot be guaranteed by the manufacturer as it has no control over the conditions under which its products are applied.

For help or more information contact our Customer Relations Team on 0845 372 3425. Before using this product please ensure you have the latest information. The information is correct at date of issue November 2013.

Sandtex
TRADE

Sandtex Trade

Hollins Road, Darwen, Lancs BB3 0BG

Tel: 0845 372 3425 Fax: 0845 372 3426 Email: info@sandtextrade.co.uk
Website: www.sandtextrade.co.uk