

## FUNGICIDE

A concentrated water-borne fungicide solution for the treatment of organic growth on exterior undecorated and all previously decorated masonry surfaces. Approved under the Control of Pesticides Regulations 1966 for use as directed. HSE Certificate No. 5258

### AVAILABILITY

**Colour range** Not applicable.

**Packaging** 1 and 5 litre.

### PROPERTIES

**Drying time** Leave for 24 hours then rinse with clean water and allow to dry.

**Composition** Sodium hypochlorite 4.6%w/w (50 grammes per litre).

**Spreading rate** 20 - 30m<sup>2</sup> per litre when diluted depending on surface suction. On textured surface the spreading rate will vary down to approx. 10m<sup>2</sup> per litre.

**Wet film thickness** Not applicable. Ensure that affected areas are well saturated during application.

**Dry film thickness** Not applicable

**Volume solids** Not applicable

**Flash point** Not applicable.

**VOC content** Not applicable.

**Limitations** Do not apply if there is a risk of rain or frost, use as a paint additive, mix with other chemicals, or apply by power spray machines. Sandtex Fungicide is a surface treatment and does not provide preservation properties to any substrate.

### PREPARATION

#### Undecorated surfaces

All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Remove all organic growth by scraping or brushing with a stiff bristle brush (not wire). Heavy long established growth is best removed by pressure washing between 1500-2000 psi (102-136 bar), wet or dry grit blasting. Care must be taken not to damage the underlying surface. The spores must be killed with an application of Sandtex Trade Fungicide diluted one volume of Fungicide with up to two volumes clean water. Leave for 24 hours and rinse with clean water. Allow to dry.

#### Previously decorated surfaces

All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect material by scraping or brushing with a stiff bristle brush (not wire) to a sound edge. Remove all organic growth by scraping or brushing with a stiff bristle brush (not wire). Heavy long established growth is best removed by pressure washing between 1500-2000 psi (102-136 bar), wet or dry grit blasting. Care must be taken not to damage the underlying surface. The spores must be killed with an application of Sandtex Trade Fungicide diluted one volume of Fungicide with up to two volumes clean water. Leave for 24 hours and rinse with clean water. Allow to dry.

**COATING SYSTEM** One application. When growth has been severe a second application may be necessary.

**APPLICATION** Apply liberally using a synthetic bristle brush and scrub well into the surface.

**CLEANING** Wash with clean water immediately after use.

**HEALTH AND SAFETY** Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing the surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Sandtex products are freely available from the place of purchase or the address below. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

#### **GENERAL INFORMATION**

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Final results cannot be guaranteed by the manufacturer as it has no control over the conditions under which its products are applied.

For help or more information contact our Customer Relations Team on 0845 372 3425. Before using this product please ensure you have the latest information. The information is correct at date of issue July 2008.



#### **Sandtex Trade**

Hollins Road, Darwen, Lancs BB3 0BG

Tel: 0845 372 3425 Fax: 0845 372 3426 Email: [info@sandtextrade.co.uk](mailto:info@sandtextrade.co.uk)

Website: [www.sandtextrade.co.uk](http://www.sandtextrade.co.uk)