

Gripsure Pro Contemporary Specification

Slip resistance

Gripsure Pro Contemporary decking profile using two inserts will achieve a minimum PTV value of 85 (pendulum test value). Gripsure non slip decking has been independently tested using the pendulum test (the operation and calibration of which are described in BS7976:2002 parts 1 and 3) operated to the United Kingdom Slip Resistance Group (UKSRG).

.....

Aggregate inserts

Gripsure Pro Contemporary decking uses a 0.5mm - 1.4mm double washed and screened Guyanan Calcined Bauxite – grey colour with a minimum PSV (polished stone value) of 70.

.....

Timber board

Gripsure Pro Contemporary uses slow grown Northern European fifths grade redwood. Growth rings will be seen to be closer together when comparing with home grown or faster grown products. The close grain offers excellent working properties for machining to profile and is much less liable to splitting or cracking. In addition, the moisture content and cell structure of redwood allows for better penetration of TANALITH[®] E preservative treatment.

Gripsure Pro Contemporary is supplied with FSC timber – Certificate No TT-COC-003864.

Gripsure Pro Contemporary board profile dimensions are ex 150mm width x 32mm depth, giving a finished product profile of approx 145mm x 28mm. Standard lengths available are 2.4m, 3.6m or 4.8m. A bespoke cutting service is available for any lengths.

Gripsure Pro Contemporary is vacuum/pressure treated with TANALITH[®] E preservative to meet the requirements of Use Class 3.2 (BS EN 335), which gives 15 year in service life.

.....

Maintenance

Gripsure Pro Contemporary is a low maintenance product, no further preservative treatment is necessary. The green/brown colour finish will fade over time to a lighter sun bleached finish.

Gripsure Pro Contemporary can be stained or painted, or water repellent sealant can be applied every 12 months to give extra protection to the timber.

Gripsure Pro Contemporary is pressure washable – it is recommended to remove dirt and mould build up across the surface of the board and inserts every 12 months, using a 150bar water pressure washer with fan nozzle at minimum distance of 150mm.

.....

Cross cut components

Any cuts, notches or drill holes to Gripsure Pro Contemporary decking during construction must be treated with Ensele end-grain preservative to maintain the integrity of the TANALITH[®] E treatment, and the 15 year in service life.