

GripsureHome - Specification

Slip resistance

GripsureHome non slip decking has been developed specifically for residential use. Being softer underfoot than conventional non slip boards, it still achieves excellent slip resistance. With two narrow non slip inserts the board retains all the classic natural looks of timber without compromising performance.

GripsureHome has been independently tested using the pendulum test (the operation and calibration of which are described in BS7976:2002 parts 1 and 3) operated to the United Kingdom Slip Resistance Group (UKSRG) guidelines and achieves a minimum 70 PTV (pendulum test value).

Aggregate inserts

GripsureHome uses a unique aggregate blend, based on 0.5mm - 0.9mm Guyanan Calcined Bauxite – grey colour with a minimum PSV (polished stone value) of 70.

GripsureHome inserts are guaranteed for 3 years from delamination or debonding from the timber board.

Timber board

GripsureHome uses slow grown Scandinavian Redwood timber. Growth rings will be seen to be closer together when comparing with home grown or faster grown products. The close grain offers excellent working properties for machining to profile and is much less liable to splitting or cracking. In addition, the moisture content and cell structure of redwood allows for better penetration of TANALITH® E preservative treatment.

GripsureHome is FSC accredited timber with profile dimensions of ex 125mm width x 32mm depth, giving a finished product profile of approx 120mm x 28mm. Lengths available are 3.6m/4.8m. A bespoke cutting service is available for other lengths.

GripsureHome is vacuum/pressure treated with TANALITH® E preservative to meet the requirements of Use Class 3.2 (BS EN 335), which gives 15 year in service life.

Maintenance

GripsureHome is a low maintenance product, no further preservative treatment is necessary. The green/brown colour finish of the timber will fade over time to a lighter sun bleached finish.

GripsureHome can be stained or painted, or water repellent sealant can be applied every 12 months to give extra protection to the timber.

GripsureHome is pressure washable – it is recommended to remove dirt and mould build up across the surface of the board and inserts every 12 months, using a 150bar water pressure washer with fan nozzle at minimum distance of 150mm.

Cross cut components

Any cuts, notches or drill holes to GripsureHome decking during construction must be treated with an end grain preservative to maintain the integrity of the TANALITH® E treatment, and the 15 year in service life.

Contact us for more information today.

 01726 844616

 info@gripsure.co.uk

www.gripsure.co.uk

Unit 2, Rockhill Business Park, Bugle, Cornwall, PL26 8RA