



GripsurePro Classic - Specification

Slip resistance

GripsurePro Classic decking profile using three inserts will achieve a minimum PTV value of 100 (pendulum test value – see below).

GripsurePro Classic has been independently tested using the pendulum test (the operation and calibration of which are described in BS7976:2002 parts 1 and 3) operated to the United Kingdom Slip Resistance Group (UKSRG) guidelines see DOWNLOADS for full results.

Aggregate inserts

GripsurePro Classic uses a 0.5mm -1.4mm double washed and screened Guyanan Calcined Bauxite – grey colour with a minimum PSV (polished stone value) of 70.

Timber board

GripsurePro Classic use slow grown Northern European fifth grade redwood. Growth rings will be seen to be closer together when comparing with home grown or faster grown products. The close grain offers excellent working properties for machining to profile and is much less liable to splitting or cracking. In addition, the moisture content and cell structure of redwood allows for better penetration of TANALITH® E preservative treatment.

GripsurePro Classic is supplied with FSC timber – Certificate No TT-COC-003864

GripsurePro Classic board profile dimensions are ex 150mm width x 32mm depth, giving a finished product profile of approx 145mm x 28mm. Standard lengths available are 2.4m, 3.6m or 4.8m. A bespoke cutting service is available for any lengths.

GripsurePro Classic is vacuum/pressure treated with TANALITH® E preservative to meet the requirements of Use Class 3.2 (BS EN 335), which gives 15 year in service life – see DOWNLOADS for further information
GripsurePro Classic is also available with preservative treatment that complies with the Highways Agency Sector 4 Scheme, which gives 30 year in service life – please specify ‘Sector 4’.

Maintenance

GripsurePro Classic is a low maintenance product, no further preservative treatment is necessary. The green/brown colour finish will fade over time to a lighter sun bleached finish. GripsurePro Classic can be stained or painted, or water repellent sealant can be applied every 12 months to give extra protection to the timber.

GripsurePro Classic is pressure washable – it is recommended to remove dirt and mould build up across the surface of the board and inserts every 12 months, using a 150bar water pressure washer with fan nozzle at minimum distance of 150mm.

Cross cut components

Any cuts, notches or drill holes to GripsurePro Classic decking during construction must be treated with Ensele end-grain preservative to maintain the integrity of the TANALITH® E treatment, and the 15 year in service life.

Contact us for more information today.

☎ 01726 844616

✉ info@gripsure.co.uk

www.gripsure.co.uk