

SLIP RESISTANCE SPECIFICATION



Gripsure® anti slip decking has been independently tested by a UKAS accredited laboratory.

The suites of tests are conducted under the UK Slip Resistance Guidelines, November 2005, and require samples of the decking board to be tested using a calibrated rubber slider. The decking is tested both under dry and wet conditions. The results achieved are then expressed as a 'PTV' number (pendulum test value).

The current guidelines suggest the following:

PTV

00 to 24 high potential for slip
25 to 35 moderate potential for slip
35 to 65 low potential for slip
65 + extremely low potential for slip

Gripsure® results 3 anti-slip inserts 150mm x 38mm profile

Dry	99 parallel test direction
	102 diagonal test direction
Wet	95 parallel test direction
	95 diagonal test direction

Conclusion

Gripsure® anti slip decking far exceeds the highest PTV value as quoted by the UK Slip Resistance Group, making the decking a very suitable and safe solution for all types of decking applications.

Contact us for more information today.

01726 844616

info@gripsure.co.uk

www.gripsure.co.uk

Unit 2, Rockhill Business Park, Bugle, Cornwall, PL26 8RA