


Movement Joints: MJ10



Locally manufactured from recycled plastic, Renderplas PVCu movement joint / expansion joint beads are designed for areas of render over 20 square metres and should be specified every 4-6 metres, over structural movement joints and changes of background. Discreet but strong, all beading gives a perfect finish to through colour render and is equally suitable for sand and cement

Performance: design data

| | | | |
|---------------------|--|--------------------------|--|
| Affiliations | Federation of Plasterers and Drywall Contractors | Fire | Class 1Y. Combustible within fire source, self extinguishing upon removal of flame, will not contribute to the combustion of the system |
| Applications | Horizontally or vertically on all standard rendering applications, external wall insulation systems, timber frame; as a day joint to divide rendered sections; at changes to background material | Health and Safety | PVCu beads are safe to handle removing the dangers of cut metal; suitable for prisons and schools |
| Chemical | Zero chemical reaction with water, sand and cement, acrylic render, water based paint; avoid organic solvents, chlorate bleach, strong acids and alkalis | Heat | Ideal for all habitable climates |
| Durability | Impact resistant; dissipates shock waves; outlasts metal; cleaned in same way as render | Guarantees | Fit for purpose for the lifetime of the render and at least 25 years |
| Economics | PVCu beads are a fraction of the price of stainless steel; added value over galvanized steel as PVCu beads are guaranteed not to stain or corrode and can reduce installation time. Reduction of impact damage | Mechanics | Flexible plastic membrane gives a certified range of +/- 2.5mm which exceeds British Standard for thermal movement (BS EN 13658-2:2005). Protective tear off strip allows quick removal of render from the joint |
| Environment | Fit for purpose for the lifetime of the render and at least 25 years | Pollution | Ecologically benign; non-hazardous in water; non-hazardous if ingested; does not release substances into the atmosphere |
| | | Strength | PVCu beads offer sufficient strength for these applications. The chemical bond between flexible and rigid parts prevents separation |
| | | Weather | Flexible plastic membrane provides a watertight seal. Not affected by weather and should be specified in all regions of high moisture or high salt |

Specification: standard data

| | | | |
|------------------------|--|---------------------------|--|
| Type | MJ10 | Weight (kg/100m) | 7.8 |
| Authority | BBA certified; manufactured to ISO 9001:2000; complies with BS EN 13914-1&2:2005; fire tested to BS 476; complies with REACH | Stock Colours | White, Ivory |
| Brand Names | Renderplas | Length | 2.5m |
| Description | 10mm PVCu Movement Joint Beads (Expansion Joints) | Packaging | 25 lengths in triwall fibreboard box |
| Composition | Exterior grade impact resistant UV stable unplasticised PVCu | Format | Cut lengths |
| Dimensions (mm) | 13mm exposed width and 25mm wings each side | Price (£/100m) | |
| Depth (mm) | 10-12mm render depth | Recycled Content % | 90.5% |
| | | Light | UV stable; any discoloration is uniform over a single facade and within industry standards |

Site works

| | | | |
|---------------------|--|----------------|---|
| Installation | Standard industry practice and tools can be used. Large irregularities in the substrate should be dubbed out and allowed to set hard prior to application. Cut to length with tin snips or fine tooth saw. Fixing with a continuous line of adhesive mortar is preferred on blockwork, or alternatively a bed of render. Non-corrosive mechanical fixings can be used as well but are not required. With external wall insulation, non-corrosive fixings alone are sufficient. | Storage | Store vertically out of direct sunlight or extreme temperatures. Can be stored flat if supported along entire length |
| | | Supply | Ex-stock next day delivery to site through extensive supply chain or direct from www.renderplas.co.uk |