



# Intraplast®/Intracrete

## Grouting Admixtures

### Technical Data Sheet

#### DESCRIPTION

**Intraplast A** is for use in cementitious grouts

**Intraplast Z** is for use in sand/cement grouts

**Intracrete** is for use in cementitious grouts

#### ADVANTAGES

- \* Expanding admixture to compensate for shrinkage
- \* Plasticising to improve strength and durability
- \* Improved fluidity and handling
- \* Can be used with the Sikament range of Superplasticisers

#### BENEFITS:

**Intraplast A** and **Z** are hydrogen based.

**Intraplast A** is designed to work with cementitious grouts only.

**Intraplast Z** is designed for use in grouts containing fine aggregates or filler materials.

**Intracrete** is nitrogen based and patented for specific use in pre-stressed and post tensioned grouting applications. The reaction produces a slow release prior to hardening.

#### Technical Data (typical)

<b>Form:</b>	Powder
<b>Colour:</b>	Intraplast A – Light Grey Intraplast Z – White Intracrete – White
<b>Chloride Content % w/w:</b>	Nil (ie less than 0.1% w/w)
<b>Suitability:</b>	All Portland Cement Types

All above values are approximate.



## METHOD OF USE

For more information on Sika visit [www.barbourproductsearch.info](http://www.barbourproductsearch.info)

In order to obtain optimum results **Intraplast A & Z** and **Intracrete** should be dispensed with the mix water.

## PACK SIZE

**Intraplast a** – 30 by 0.5 Kg packs

**Intraplast Z** – 4 by 1.5 Kg packs

**Intracrete** – 20 by 1.0 Kg packs

## DOSAGE

**Intraplast A** is dosed at 1% BWC

**Intraplast Z** is dosed at 3% BWC

**Intracrete** is dosed at 2% BWC

## STORAGE AND SHELF LIFE

**Intraplast/Intracrete** should be stored in dry conditions above 0°C in original sealed containers.

The shelf life of **Intraplast/Intracrete** under these conditions is a minimum of 12 months.



### Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

### Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

**Please consult our Technical Sales Department for further information**

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: [sika@uk.sika.com](mailto:sika@uk.sika.com)

Fax: 01707 329129 [www.sika.com](http://www.sika.com)





# Sikatard® R/Sikanol® M

## Retarder and Air Entraining Agent for Ready to Use Mortar

### Technical Data Sheet

#### DESCRIPTION

**Sikatard R/Sikanol M** is a two component plasticising and stabilising system which delays the set of sand/cement and cement/lime/sand mortars for extended periods while improving workability, reducing bleed water and improving frost resistance.

#### USES

- \* **Sikatard R/Sikanol M** are used in conjunction to provide masonry mortars for laying bricks manufactured from absorbent materials such as clay, sand-lime and for concrete blocks.
- \* Suitable for both ready mix and site batch operation.

#### ADVANTAGES

- \* **Sikanol M** increases the plasticity of the mortar by the entrainment of controlled amounts of air. **Sikanol M** also improves cohesion and consistency.
- \* The reduced water content can lead to increased compressive strength.
- \* **Sikatard R** delays the set of the mortar; however, the set retarding effect declines once in place as moisture evaporates and migrates due to suction enabling setting and curing to occur as normal.
- \* Mortar remains workable for 36 hours or more depending on dosage of **Sikatard R**.

#### Technical Data (typical)

<b>Form:</b>	Liquid
<b>Colour:</b>	Brown
<b>Specific Gravity:</b>	R = 1.17    M = 1.05
<b>Chloride Content</b>	Nil

All above values are approximate.



**METHOD OF USE**

Dosage rates to achieve the desired working life will depend on the class of mortar required for the application (to BS4721), ambient temperature, sand quality and the desired workability. The admixtures must be added separately into the mixing water. They must not be pre-mixed, nor may they be added to dry mix components. Thorough mixing is essential. Mixing should continue until a uniform consistency is achieved.

Sands must comply with the relevant British Standard. Fresh mortar must be contained in a polytub or similar container, a layer of water placed on top in order to prevent drying out and the storage containers covered.

Sands for masonry mortars must be evaluated for their suitability for retarded mortars. Sands containing a high silt content may not be suitable.

**DISPENSING**

**Sikatard R** 0.5–1.5% by weight of cement

**Sikanol M** 0.15–0.45% by weight of cement

The correct dosage for the required retardation is best achieved by site trials with the actual materials and mix design. The dosage may require an increase for lime/sand combinations.

Typically 2.5 litres **Sikatard R** and 1.0 litre **Sikanol M** per cubic metre for a Class III mortar.

**COMPATIBILITY**

**Sika Admixtures:** All  
**Cements:** All

**IMPORTANT NOTES**

**Sikatard R** and **Sikanol M** conform to BS4887: 'Mortar Admixtures'

Part 1: Specification for air entraining (plasticising) admixtures

Part 2: Specification for set retarding admixture

If bricks/blocks etc are saturated, moisture migration from the mortar will be reduced and setting/ curing delayed.

**PACKAGING**

Refer to latest price list

**STORAGE AND SHELF LIFE**

Minimum 1 year in sealed containers stored in dry warehouse condition (+5°C – +25°C). Protect from frost.



**Handling Precautions**

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

**Important Note**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

**Please consult our Technical Sales Department for further information**

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: [sika@uk.sika.com](mailto:sika@uk.sika.com)

Fax: 01707 329129 [www.sika.com](http://www.sika.com)

