

# String Theory Interval

## Technical Specification

SIN-TS-20170515-01-GB

**amtico**  
carpet

Name	Standard	Symbol	Result
CE / DOP	EN 14041		CPR/A1/015
Usage Classification	EN 1307		23, 33
Luxury Class	EN 1307		LC1
Size	EN 994		609.6 x 609.6 mm (24" x 24")
Construction Gauge	ISO 2424		Textured Patterned Loop 1/10"
Fibre Composition	-		Stringworks Nylon 6,6 (30% post-production recycled)
Dye Method	-		Yarn & Solution dyed
Primary Backing	-		Non-Woven Polyester/Polyamide
Secondary Backing	-		PVC
Stitches per 10cm	-		34
Total Thickness (mm)	ISO 1765		6.0 mm
Total Mass Per Unit Area (g/m <sup>2</sup> )	ISO 8543		4457 g/m <sup>2</sup>
Effective Pile Thickness (mm)	ISO 8543		2.35 mm
Pile Mass Total/Effective (g/m <sup>2</sup> )	ISO 8543		543/359 g/m <sup>2</sup>
Surface Pile Density (g/m <sup>3</sup> )	ISO 8543		0.15 g/m <sup>3</sup>
Number of Tufts/Loops (calculated per m <sup>2</sup> )	ISO 1763		140 290
Fire Resistance	EN 13501-1		C <sub>fl</sub> -s1
Slip Resistance	EN 13893		Class DS
Dimension Stability	EN 986		≤ 0.2 %
Anti-Static Body Voltage (kV @25%rh)	ISO 6356		≤ 2.0 kV
Vertical Electric Resistance	ISO 10965		≥ 10 <sup>10</sup> Ω
Horizontal Electric Resistance	ISO 10965		≥ 10 <sup>10</sup> Ω
Castor Chair Suitability	EN 985		r ≥ 2.4 / Intensive Use
Light Colour Fastness	EN ISO105:B02		≥ 6
Colour Fastness to Rubbing	EN ISO 105:X12		4/5
Colour Fastness to Water	EN ISO 105:E01		5
Resistance to Fraying	EN 1814		Pass
Impact Sound Insulation ΔL <sub>w</sub>	EN ISO 717-2		25 dB
Sound Absorption	EN ISO 11654 ISO 354		α <sub>w</sub> = 0.15 Hz 125 250 500 1000 2000 4000 α <sub>w</sub> 0.00 0.03 0.02 0.18 0.33 0.46
Thermal Resistance (m <sup>2</sup> K/W)	ISO 8302		0.065 m <sup>2</sup> K/W
Emissions COV			A+
Emissions			Certified / www.m1.rts.fi
Emissions		AgBB	Pass
Emissions		Belgium VOC	Pass
Environment	ISO 14025		Mannington decl. no EPD 10017