

Sheathing Felt (PASDS 03)Product Ref: (DsC8-0505)
Issue No: 02**COMPOSITION/INFORMATION ON INGREDIENTS**

The product comprises a batt of jute fibre, which is impregnated with bitumen. The surface is dusted with powdered limestone. It is not classified as dangerous under The Chemicals (Hazard Information and Packaging for supply) Regulations 1994, (CHIP 2) as amended.

Substance	Occupational Exposure	Standard
	Long-term exposure limit 8-hour TWA	Short-term Exposure Limit 15 min ref period
Limestone	10 mg/m ³ total inhalable dust 4 mg/m ³ respirable dust	
Asphalt, petroleum fumes	5 mg/m ³	10 mg/m ³

NOTE: Long-term exposure to concentration levels above OES values may result in adverse health effects.

HAZARDS IDENTIFICATION

The product is not hazardous to health in normal use. The only hazards associated with the product are during the subsequent laying of mastic asphalt.

FIRST-AID MEASURES

IN ALL CASES, IF SYMPTOMS ARE SEVERE, PERSIST OR CAUSE CONCERN, OBTAIN IMMEDIATE MEDICAL ADVICE

First aid procedures apply when products are subjected to high temperatures, e.g., during the laying of mastic asphalt or in a fire.

Skin: In the event of contact with hot mastic asphalt, immediately cool affected part under cold running water for at least 10 minutes. Adhering mastic asphalt can be left to act as a sterile barrier, which will detach itself after a few days or may be removed using warm medicinal liquid paraffin. Do not use solvents. All burns should receive medical attention.

Eyes: Hot asphalt splashed into the eye should be cooled immediately by irrigating with cold running water for 10-15 minutes. In the event of any product remaining, try to remove only by continued irrigation with water - obtain immediate medical attention.

Inhalation: Remove from source of fumes to fresh air if any ill effects are experienced. Rest and keep warm.

FIRE-FIGHTING MEASURES

In the event of a fire, wear protective clothing. In confined areas, fire fighters should wear self-contained breathing apparatus. Extinguish fire with foam, dry powder, water fog, sand or earth. Do not use water jets.

ACCIDENTAL RELEASE MEASURES

Not applicable.

Langley Waterproofing Systems Limited

Bishop Crewe House, North Street, Daventry, Northants. NN11 4GH

Tel: 01327 704778 Fax: 01327 704845 www.langley.co.uk

Sheathing Felt (PASDS 03)

Product Ref: (DsC8-0505)
Issue No: 02

HANDLING AND STORAGE

Store under cover away from sources of heat and ignition.

EXPOSURE CONTROLS/PERSONAL PROTECTION

The use of heavy-duty gloves to protect against skin abrasion during installation is recommended.

PHYSICAL AND CHEMICAL PROPERTIES

Langley Black Sheathing Felt is supplied for use as a separating layer in mastic asphalt roofing systems. It is supplied in roll form for loose laying on top of the decking material, or insulation layer if used, prior to application of the mastic asphalt. The product is also used in flooring applications. Additional product information including details of physical characteristics is available on request.

STABILITY AND REACTIVITY

No known hazard.

TOXICOLOGICAL INFORMATION

No known hazard.

ECOLOGICAL INFORMATION

No data available.

DISPOSAL CONSIDERATIONS

Disposed of waste material in accordance with national and local regulations.

TRANSPORT INFORMATION

Not classified as dangerous for transport.

REGULATORY INFORMATION

Not classified as hazardous for supply. No statutory label required.

The information contained in this data sheet does not constitute an assessment of workplace risk as required by current legislation. Whilst every care is taken to see that the information is correct and up to date, it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded.

Langley Waterproofing Systems Limited

Bishop Crewe House, North Street, Daventry, Northants. NN11 4GH

Tel: 01327 704778 Fax: 01327 704845 www.langley.co.uk