

90g



Breathable membrane

for use on all type of domestic and commercial roofing and walling applications, including

- cold non vented,
- traditional hybrid,
- cold vented,
- Scottish and fully boarded applications.

ECO



Available in:
1x20m (1.9kg)
1x50m (4.6kg) 83 per pallet
1.5x50m (6.9kg) 35 per pallet



PERMAVENT-ECO

Weight, g/m ²	90
Water tightness, class	w1
Water vapour transmission (sd), m	0.02
Maximum tensile force (MD), N/50mm	200
Maximum tensile force (CD), N/50mm	150
Elongation at max. tensile force (MD), %	65
Elongation at max. tensile force (CD), %	55
Resistance to tearing MD (nail shank), N	100
Resistance to tearing CD (nail shank), N	90
Vapour resistance, MNsg ⁻¹	0.11

Permavent use the very latest technology from the medical industry to encapsulate the highest grade hydrophobic film inside the very highest quality spunbond polypropylene layers. Unlike other companies, who simply stick the different layers together, Permavent membranes are manufactured in a single process that greatly improves the quality and integrity of our membranes. This 3 in 1 process means that Permavent offer the best performing breather membranes in their class with superior strength, breathability, flexibility and durability.

Permavent-ECO is fully tested and certified

BBA 05/4227 conventional and warm roofing (British Board of Agreement).

BBA 06/4311 cold non-vented roofing (British Board of Agreement).

IAB 06/0244 Fully certified by the IAB (Irish Agreement Board).

Permavent-ECO is also fully certified under the CE having been tested and certified by independent European laboratories and is only manufactured under the strictest ISO requirements.

Permavent Membranes are certified for use in all types of roofing and walling applications and conform fully with

BS 5250: 2011 Code of practice for control of condensation in buildings.

BS 5534: 2003 +A1 2010 Code of practice for slating and Tiling.

BS 8000-6: 1990 Workmanship on building sites.

BS EN 1991-1-4; 2005 +A1: 2010 +UK NA.

BS EN 13859: Flexible sheets for Underlays.

BS EN 13501-1 2007.

